

SD TAR ENAMEL QD

快干沥青漆

PRODUCT DESCRIPTION 产品简介	A quick drying bituminous anticorrosive paint based on bituminous binder reinforced with special synthetic resin 由特殊合成树脂制成的快干沥青涂料。	
RECOMMENDED USE 用途	For engine room or pump room' s tank top, bilge well, chain lockers, anchor chains, battery room' s decks rudder interiors, stern part, etc. 用于机舱和泵舱的内底, 污水井、锚链舱、锚链、电池间甲板、舵叶内部、船艏等	
FEATURES 产品特性	Quick drying 干燥迅速 Excellent resistance to water and galvanic action 极好的耐水、耐电化学腐蚀性 Outstanding adhesion properties to bare steel substrates 同裸钢底材附着力良好 Good workability 良好的施工性能	
PHYSICAL PROPERTIES 基本数据		
Color 颜色	Black 黑色	
Volume Solids 体积固体份	65%	
VOC 挥发性有机化合物含量	496g/L 496克/升	
Flash Point 闪点	Greater than 27°C 27°C以上	
Film thickness 涂装膜厚	Dry: 50–150 microns/coat 干膜: 50–150微米/道	Wet : 77–230micat/coat 湿膜: 77–230微米/道
Theoretical Coverage 理论涂布率	6.5m ² /Ltr/100 microns 6.5平方米/升/100 μ m Practical coverage depending on surface conditions, environment, applications, etc. 实际涂覆率与表面处理, 外界环境, 施工方法等多种因素有关。	

APPLICATION

施工

Application Temperature

施工温度

-10℃-40℃

Application Methods

施工方法

Airless spray, air spray and roller

无气喷涂、空气喷涂、滚涂

Airless spray 无气喷涂

Nozzle tip	喷嘴尺寸	0.43mm-0.53mm
Nozzle pressure	出口压力	≥10Mpa
Thinning ratio	稀释比率	0-10% by volume (体积比)

Roller 滚涂

Thinning ratio	稀释比率	5-10% by volume (体积比)
----------------	------	-----------------------

Thinner

稀释剂

SD Tar Enamel QD Thinner

专用稀释剂

Drying time &

Overcoating interval

干燥时间&涂装间隔

Temperature	温度	-5℃	5℃	10℃	20℃	30℃
Surface dry	指触干燥	6hrs	4hrs	3hrs	1hr	1hr
Touch dry	半硬干燥	40hrs	30hrs	24hrs	16hrs	12hrs
Min. interval	最小涂装间隔	40hrs	30hrs	24hrs	16hrs	12hrs
Max. interval	最大涂装间隔	—	—	—	—	—

Applied substrates

适用底材

Bare steel.

裸钢

STORAGE

贮存

Store in dry, cool condition and away from sources of heat and ignition. Containers must be kept tightly closed.

贮存于干燥阴凉的环境中，远离热源及火源。包装桶必须保持封闭。

Shelf life

贮存期限

12months from date of production (25℃)

自生产之日起12个月 (25℃)

DISCLAIMER

提请注意

The information given on this sheet is to the best of our knowledge and accurate at the time of issuing. Since conditions of use are beyond the manufacturer's control, information contained herein is without warranty, implied or otherwise, and the suitability of the material for the use contemplated is the sole responsibility of the buyer. The information contained on this data sheet is subject to modification at any time due to our policy of modification and product development. Please check this data sheet is current prior to using the product.

本说明书所提供信息均为目前我方所掌握最全面正确的资料,鉴于产品使用条件非我方所能控制,此中信息不含担保,即仅在选取产品上对买方负责。由于我公司产品及生产工艺的不断发展,本说明书的内容也会随时进行更改,此中所有信息均以我方确认为主。产品使用前,请确认所持说明书为最新版本。