

THERMO 300 PRIMER 有机硅耐热底漆 300

PRODUCT DESCRIPTION 产品简介	A heat resisting paint based on modified silicone resin 由改性有机硅树脂组成的耐热涂料。	
RECOMMENDED USE 用途	As a primer for long-term protection of hot pipelines, exhaust pipes, smoke stacks and other hot surfaces at temperatures up to 300°C and 350°C at a short time. 作为底漆长效保护温度高达300°C（瞬时温度350°C）的热管道、排气管、烟囱和其它热表面。	
FEATURES 产品特性	Excellent heat resistance (Up to 300°C) 极好的耐热性（达到300°C） Good weathering resistance 良好的耐候性 Good applicability 良好的施工性能	
PHYSICAL PROPERTIES 基本数据		
Color 颜色	Black 黑色	
Volume Solids 体积固体份	45%	
VOC 挥发性有机化合物含量	519g/L 519克/升	
Flash Point 闪点	Greater than 9°C 9°C以上	
Film thickness 涂装膜厚	Dry : 20–30 microns/coat 干膜: 20–30 微米/道	Wet :44–67microns/coat 湿膜: 44–67微米/道
Theoretical Coverage 理论涂布率	22.5m ² /Ltr/20 microns 22.5平方米/升/20 μm Practical coverage depending on surface conditions, environment, applications, etc. 实际涂布率与表面处理, 外界环境, 施工方法等多种因素有关。	
APPLICATION 施工		
Application Temperature 施工温度	–5°C–40°C	
Mixing 混合	Mix thoroughly with power agitator 使用动力工具搅拌均匀	

Mixing Ratio
混合比例

One component coating
单组份涂料

Application Methods
施工方法

Airless spray, air spray, brush and roller
无气喷涂、空气喷涂、刷涂、滚涂

Airless spray 无气喷涂

Nozzle tip	喷嘴尺寸	0.33mm-0.43mm
Nozzle pressure	出口压力	≥ 10Mpa
Thinning ratio	稀释比率	0-5% by volume (体积比)

Brush/Roller 刷涂、滚涂

Thinning ratio	稀释比率	0-5% by volume (体积比)
----------------	------	------------------------

Thinner
稀释剂

Paint Thinner X
稀释剂X

Drying time &
Overcoating interval
干燥时间&涂装间隔

Temperature	温度	5℃	20℃	30℃
Surface dry	指触干燥	3hrs	1hr	1hr
Touch dry	半硬干燥	5hrs	3hrs	3hrs
Min. interval	最小涂装间隔	16hrs	12hrs	8hrs
Max. interval	最大涂装间隔	—	—	—

Full cure: must bake in 200℃-250℃ for 1hr
完全固化：必须在200℃~250℃烘烤1小时

Typical undercoat
适用下涂

SD Zine Primer 1500, or according to the coating system of Cosco Kansai.
环氧富锌底漆1500，或参考我司涂装配套

Typical topcoat
适用上涂

Thermo 300 Finish
有机硅耐热面漆300

STORAGE
贮存

Store in dry, cool condition and away from sources of heat and ignition. Containers must be kept tightly closed.
贮存于干燥阴凉的环境中，远离热源及火源。包装桶必须保持封闭。

Shelf life
贮存期限

12months from date of production (25℃)
自生产之日起12个月 (25℃)

DISCLAIMER
提请注意

The information given on this sheet is to the best of our knowledge and accurate at the time of issuing. Since conditions of use are beyond the manufacturer' s control, information contained herein is without warranty, implied or otherwise, and the suitability of the material for the use contemplated is the sole responsibility of the buyer. The information contained on this data sheet is subject to modification at any time due to our policy of modification and product development. Please check this date sheet is current prior to using the product.

本说明书所提供信息均为目前我方所掌握最全面正确的资料,鉴于产品使用条件非我方所能控制，此中信息不含担保，即仅在选取产品上对买方负责。由于我公司产品及生产工艺的不断发展，本说明书的内容也会随时进行更改，此中所有信息均以我方确认为主。产品使用前，请确认所持说明书为最新版本。