

RABAMARINE BTB

氯化橡胶面漆

PRODUCT DESCRIPTION 产品简介	A chlorinated rubber universal finish 适用型氯化橡胶面漆。	
RECOMMENDED USE 用途	As a finish for steel structure. in immersion and non immersion areas. 作为钢结构表面的面漆使用,用于浸没和非浸没区域。	
FEATURES 产品特性	Good weathering properties 良好的耐候性 High resistance to sea water and oil 良好的耐海水性和耐油性 Excellent abrasion resistance 极好的耐磨性 Compatibility with all various coating systems 适用于各种涂装配套 Quick drying 干燥迅速	
PHYSICAL PROPERTIES 基本数据		
Color 颜色	Colors 各色	
Volume Solids 体积固体份	46%	
VOC 挥发性有机化合物含量	510g/L 510克/升	
Flash Point 闪点	Greater than 25°C 25°C以上	
Film thickness 涂装膜厚	Dry : 30-50 microns/coat 干膜: 30-50微米/道	Wet : 65-109microns/coat 湿膜: 65-109微米/道
Theoretical Coverage 理论涂布率	11.5m ² /L/40 microns 11.5平方米/升/40 μm Practical coverage depending on surface conditions, environment, applications, etc. 实际涂布率与表面处理, 外界环境, 施工方法等多种因素有关。	
APPLICATION 施工		
Application Temperature 施工温度	-10°C-40°C	
Mixing 混合	Mix thoroughly with power agitator 使用动力工具搅拌均匀	

Mixing Ratio
混合比例

One component coating
单组份涂料

Application Methods
施工方法

Airless spray, air spray, brush and roller
无气喷涂、空气喷涂、刷涂、滚涂

Airless spray 无气喷涂

Nozzle tip	喷嘴尺寸	0.43mm-0.53mm
Nozzle pressure	出口压力	≥ 10Mpa
Thinning ratio	稀释比率	0-10% by volume (体积比)

Brush/Roller 刷涂、滚涂

Thinning ratio	稀释比率	0-10% by volume (体积比)
----------------	------	-------------------------

Thinner
稀释剂

Rabamarine Thinner
氯化橡胶稀释剂

Drying time &
Overcoating interval
干燥时间&涂装间隔

Temperature	温度	-5℃	5℃	20℃	30℃
Surface dry	指触干燥	80mins	60mins	30mins	20mins
Touch dry	半硬干燥	10hrs	6hrs	3hrs	2hrs
Min. interval	最小涂装间隔	15hrs	12hrs	6hrs	4hrs
Max. interval	最大涂装间隔	—	—	—	—

Typical undercoat
适用下涂

Rabamarine AC, Epomarine EX 500 or according to the coating systems of Cosco Kansai.
Rabamarine AC, Epomarine EX 500或参考我司推荐配套。

STORAGE
贮存

Store in dry, cool condition and away from sources of heat and ignition. Containers must be kept tightly closed.
贮存于干燥阴凉的环境中，远离热源及火源。包装桶必须保持封闭。

Shelf life
贮存期限

12 months from date of production (25℃)
自生产之日起12个月 (25℃)

DISCLAIMER
提请注意

The information given on this sheet is to the best of our knowledge and accurate at the time of issuing. Since conditions of use are beyond the manufacturer's control, information contained herein is without warranty, implied or otherwise, and the suitability of the material for the use contemplated is the sole responsibility of the buyer. The information contained on this data sheet is subject to modification at any time due to our policy of modification and product development. Please check this data sheet is current prior to using the product.

本说明书所提供信息均为目前我方所掌握最全面正确的资料,鉴于产品使用条件非我方所能控制,此中信息不含担保,即仅在选取产品上对买方负责。由于我公司产品及生产工艺的不断发展,本说明书的内容也会随时进行更改,此中所有信息均以我方确认为主。产品使用前,请确认所持说明书为最新版本。