KANPE GLASS EP

环氧玻璃鳞片漆

PRODUCT DESCRIPTION

产品简介

A high build, two pack pure epoxy coating reinforced with

Glassflakes.

是一种采用玻璃鳞片加强的厚涂型双组份纯环氧涂料。

RECOMMENDED USE

用途

For surface subject to abrasion and highly corrosive envi-

ronment of splash zones, jetty pilings and working decks. Can be used as interior lining for crude oil tanks.

用于浸没和非浸没区域的钢结构表面,如船底,水线部位等。

在各类涂料施工前保护喷砂处理后的底材

FEATURES

产品特性

Excellent durability against acid, alkali, oils, sea water

极好的耐酸、耐碱、耐油和耐海水性

Prevent penetration of chemicals and water steam

能防止水汽或化学气体侵入

Excellent mechanical strength and excellent adhesion property

很强的机械性和附着力

PHYSICAL PROPERTIES

基本数据

Color Grey and yellow

Volume Solids

体积固体份

VOC 360g/L, accord with EU Dircrtive2004/42/EC, subcategory j

挥发性有机化合物含量 360克/升,符合欧盟溶剂排放指令2004/42/EC, j子类别

Flash Point Greater than 27℃

闪点

27℃以上

69%

Film thickness Dry: 125–400 microns/coat Wet: 181–580microns/coat

Theoretical Coverage

理论涂布率

6.9 m²/Ltr/100 microns 6.9平方米/升/100 μ m

Practical coverage depending on surface conditions,

environment, applications, etc.

实际涂布率与表面处理, 外界环境, 施工方法等多种因素有关。

APPLICATION

施工

Application Temperature

施工温度 5℃-40℃

Mixing Combine Base with Hardener, mix thoroughly with power agitator

混合 混合主剂与固化剂,使用动力工具搅拌均匀

Mixing Ratio Base/Hardener=4.1/1 (by volume)

混合比例 主剂/固化剂=4.1/1(体积比)



Pot life 混合使用期

5℃	20℃	30℃	
2.5hrs	1.5hrs	1hrs	

Application Methods 施工方法 Airless spray, air spray, brush and roller 无气喷涂、空气喷涂、刷涂、滚涂

Airless spray 无气喷涂

Nozzle tip	喷嘴尺寸	0.43mm-0.53mm ≥15Mpa		
Nozzle pressure	出口压力			
Thinning ratio	稀释比率	0-10% by volume (体积比)		

Brush/Roller 刷涂、滚涂

Thinning ratio	稀释比率	0-10% by volume (体积比)	
----------------	------	-----------------------	--

Thinner 稀释剂 Epomarine Thinner 环氧稀释剂

Drying time & Overcoating interval 干燥时间&涂装间隔

Temperature	温度	5℃	10℃	20℃	30℃
Surface dry	指触干燥	4hrs	3hr	1hr	0.5hrs
Touch dry	半硬干燥	48hrs	36hrs	16hrs	12hrs
Min. interval	最小涂装间隔	48hrs	36hrs	16hrs	12hrs
Max. interval	最大涂装间隔	7days	7days	7days	7days

Applied Substrates 适用底材

Bare steel 裸钢

STORAGE

贮存

Store in dry, cool condition and away from sources of heat and ignition. Containers must be kept tightly closed.

贮存于干燥阴凉的环境中,远离热源及火源。包装桶必须保持封闭。

Shelf life 贮存期限 12months from date of production (25℃)

自生产之日起12个月(25℃)

DISCLAIMER 提请注意 The information given on this sheet is to the best of our knowledge and accurate at the time of issuing. Since conditions of use are beyond the manufacturer's control, information contained herein is without warranty, implied or otherwise, and the suitability of the material for the use contemplated is the sole responsibility of the buyer. The information contained on this data sheet is subject to modification at any time due to our policy of modification and product development. Please check this date sheet is current prior to using the product.

本说明书所提供信息均为目前我方所掌握最全面正确的资料,鉴于产品使用条件非我方所能控制,此中信息不含担保,即仅在选取产品上对买方负责。由于我公司产品及生产工艺的不断发展,本说明书的内容也会随时进行更改,此中所有信息均以我方确认为主。产品使用前,请确认所持说明书为最新版本。



