ALKFEND FINISH 30

工二工公	_	ナカ	~
醇酸	ш	1001	11
HZHQ	IHI	12150	U

PRODUCT DESCRIPTION A finish based alkyd resin and pigments. 由醇酸树脂和着色颜料组成的醇酸面漆。 产品简介 RECOMMENDED USE For steel structure in non immersion areas. 用于非浸没区域的钢结构表面。 用途 **COMPLIED STANDARDS** Complies with GB/T 25251-2010 符合国标GB/T 25251-2010<醇酸树脂涂料标准> 符合标准 **FEATURES** High gloss and good weathering resistance 产品特性 良好的光泽和耐候性 Good abrasion resistance 良好的耐磨性 Good workability 良好的施工性能

PHYSICAL PROPERTIES

基本数据

Color Colors 颜色 各色

Finish Gloss 光泽 有光

Volume Solids

56% 体积固体份

VOC 348g/L, accord with EU Dircrtive2004/42/EC, subcategory j

挥发性有机化合物含量 348g/L,符合欧盟溶剂排放指令2004/42/EC,j子类别

Flash Point Greater than 18℃

闪点 18℃以上

Film thickness Dry: 25-40 microns/coat Wet: 45-72 microns/coat

涂装膜厚 干膜: 25-40微米/道 湿膜: 45-72微米/道

Theoretical Coverage

14.0 m²/Ltr/40 microns 理论涂布率 14.0平方米/升/40 µ m

Practical coverage depending on surface conditions, environment,

applications, etc.

实际涂布率与表面处理, 外界环境, 施工方法等多种因素有关。

APPLICATION

施工

Application Temperature

-5℃-40℃ 施工温度

Mix thoroughly with power agitator Mixing

使用动力工具搅拌均匀 混合



Mixing Ratio 混合比例

One component coating

单组份涂料

Application Methods

施工方法

Airless spray, air spray, brush and roller 无气喷涂、空气喷涂、刷涂、滚涂

Airless spray 无气喷涂

Nozzle tip	喷嘴尺寸	0.43mm-0.53mm ≥10Mpa		
Nozzle pressure	出口压力			
Thinning ratio	稀释比率	0-10% by volume (体积比)		

Brush/Roller 刷涂、滚涂

Thinning ratio 稀释比率 0-10% by volume (体积比)

Thinner 稀释剂

SD Marine Paint Thinner

醇酸稀释剂

Drying time & Overcoating interval 干燥时间&涂装间隔

Temperature	温度	-5℃	5℃	20℃	30℃
Surface dry	指触干燥	16hrs	10hrs	4hr	3hr
Touch dry	半硬干燥	48hrs	24hrs	16hrs	10hrs
Min. interval	最小涂装间隔	72hrs	48hrs	24hrs	24hrs
Max. interval	最大涂装间隔	_	-	-	_

Typical undercoat 适用下涂

Alkfend Primer 30

醇酸底漆等

Typical topcoat 适用上涂

Alkfend Finish 30 or according to the coating system of Cosco

Kansai.

醇酸面漆或参考我司涂装配套

STORAGE

贮存

Store in dry, cool condition and away from sources of heat and

ignition. Containers must be kept tightly closed.

贮存于干燥阴凉的环境中,远离热源及火源。包装桶必须保持封闭。

Shelf life 贮存期限

12 months from date of production (25°C)

自生产之日起12个月(25℃)

DISCLAIMER 提请注意

The information given on this sheet is to the best of our knowledge and accurate at the time of issuing. Since conditions of use are beyond the manufacturer's control, information contained herein is without warranty, implied or otherwise, and the suitability of the material for the use contemplated is the sole responsibility of the buyer. The information contained on this data sheet is subject to modification at any time due to our policy of modification and product development. Please check this date sheet is current prior to using the product.

本说明书所提供信息均为目前我方所掌握最全面正确的资料,鉴于产品 使用条件非我方所能控制,此中信息不含担保,即仅在选取产品上对 买方负责。由于我公司产品及生产工艺的不断发展,本说明书的内容 也会随时进行更改,此中所有信息均以我方确认为主。产品使用前,

请确认所持说明书为最新版本。

