Shin LLL No.55

防污漆 Shin LLL No.55

PRODUCT DESCRIPTION 产品简介	A tin-free antifouling paint 无锡防污漆。		
RECOMMENDED USE 用途	For ship bottoms & below water of steel structure. 用于船底及水下钢结构表面。		
FEATURES 产品特性	Long-term protection against fouling 长期防污保护 Free from organic tin compounds 不含有机锡成份 Outstanding high-build applicability 极好的厚涂性 Good workability 良好的施工性能		

PHYSICAL PROPERTIES

基本数据

Color Red and oxide Red

颜色 红色和铁红色

Volume Solids

体积固体份 52%

VOC 418g/L, accord with EU Dircrtive2004/42/EC, subcategory j

挥发性有机化合物含量 418g/L,符合欧盟溶剂排放指令2004/42/EC,j子类别

Flash Point Greater than 29℃

闪点 29℃以上

Film thickness Dry: 50-100 microns/coat Wet: 96-192 microns/coat

涂装膜厚 干膜: 50-100 μ m/道 湿膜: 96-192 μ m/道

Theoretical Coverage 6.5m²/Ltr/80 microns

理论涂布率 6.5平方米/升/80 µ m

Practical coverage depending on surface conditions, environment,

applications, etc.

实际涂布率与表面处理, 外界环境, 施工方法等多种因素有关。

APPLICATION

施工

Application Temperature

施工温度 -10℃-40℃

Mixing Mix thoroughly with power agitator

混合 使用动力工具搅拌均匀

Mixing Ratio One component coating

混合比例
单组份涂料



Application Methods 施工方法 Airless spray, air spray, brush and roller 无气喷涂、空气喷涂、刷涂、滚涂

Airless spray 无气喷涂

Nozzle tip	喷嘴尺寸	0.43mm-0.53mm ≥10Mpa		
Nozzle pressure	出口压力			
Thinning ratio	稀释比率	0-10% by volume (体积比)		

Brush/Roller 刷涂、滚涂

	Thinning ratio	稀释比率	0-10% by volume	(体积比)
--	----------------	------	-----------------	-------

Thinner 稀释剂 Rabamarine Thinner 氯化橡胶稀释剂

Drying time & Overcoating interval 干燥时间&涂装间隔

Temperature	温度	-5℃	5℃	20℃	30℃
Surface dry	指触干燥	8hrs	4hrs	1hr	0.5hr
Touch dry	半硬干燥	18hrs	12hrs	4hrs	3hrs
Min. interval	最小涂装间隔	14hrs	10hrs	5hrs	4hrs
Max. interval	最大涂装间隔	-	-	-	_

Typical undercoat 适用下涂

Rabamarine AC, Vinylia BTM (S) or according to the coating system of Cosco Kansai.

氯化橡胶底漆, 乙烯漆等, 或参考我司推荐配套

STORAGE 贮存 Store in dry, cool condition and away from sources of heat and ignition. Containers must be kept tightly closed.

贮存于干燥阴凉的环境中,远离热源及火源。包装桶必须保持封闭。

Shelf life 贮存期限 12months from date of production (25°C)

自生产之日起12个月(25℃)

DISCLAIMER 提请注意 The information given on this sheet is to the best of our knowledge and accurate at the time of issuing. Since conditions of use are beyond the manufacturer's control, information contained herein is without warranty, implied or otherwise, and the suitability of the material for the use contemplated is the sole responsibility of the buyer. The information contained on this data sheet is subject to modification at any time due to our policy of modification and product development. Please check this date sheet is current prior to using the product.

本说明书所提供信息均为目前我方所掌握最全面正确的资料,鉴于产品使用条件非我方所能控制,此中信息不含担保,即仅在选取产品上对买方负责。由于我公司产品及生产工艺的不断发展,本说明书的内容也会随时进行更改,此中所有信息均以我方确认为主。产品使用前,请确认所持说明书为最新版本。

