

UNIVERSAL MIO-50 通用环氧云铁漆 MIO-50

PRODUCT DESCRIPTION

产品简介

A low VOC, high solids, two pack high build epoxy coating with M.I.O.(Micaceous Iron Oxide)

是一种低 VOC 含量、高固体、双组份厚浆型环氧云铁涂料。

RECOMMENDED USE

用途

As a primer or intermediate coat can be used in steel structure at industrial moderately corrosive environments of new construction and maintenance .

用于中等工业腐蚀环境的新建钢结构表面，可作为底漆或中间漆使用。也可在维修配套中使用。

COMPLIED STANDARDS

符合标准

Complies with JT/T 722-2008, JT/T 733-2008

符合公路桥梁钢结构防腐涂装技术条件 JT/T 722-2008、港口机械钢结构表面防腐涂层技术条件 JT/T 733-2008

FEATURES

产品特性

Low VOC, high volume solids

低 VOC 含量，高固体份

Good anti-corrosive performance

极好的防腐性能

Excellent surface-tolerant properties

极好的表面适应性能

Tough and strong films

漆膜坚韧

Add MIO .(Micaceous Iron Oxide),can be overcoated after extended periods

添加云铁成分，适应较长时间后覆涂

PHYSICAL PROPERTIES

基本数据

Color

颜色

Grey and Oxide Red

灰色和铁红色

Volume Solids

体积固体份

78%

VOC

挥发性有机化合物含量

210g/L, accord with EU Dirertive2004/42/EC, subcategory j

210 克/升，符合欧盟溶剂排放指令 2004/42/EC, j 子类别

Flash Point

闪点

Greater than 30 °C

30 °C 以上

Film thickness

涂装膜厚

Dry 100-250 microns/coat

干膜: 100-250 微米/道

Wet : 128-320microns/coat

湿膜: 128-320 微米/道

Theoretical Coverage

理论涂覆率

0.385Kg/m²/200 microns

0.385 千克/平方米/200 微米

Practical coverage depending on surface conditions, environment, applications, etc.

实际涂覆率与表面处理，外界环境，施工方法等多种因素有关。

APPLICATION

施工

Application Temperature

施工温度

5 °C-40 °C

Mixing

混合

Combine Base with Hardener, mix thoroughly with power agitator

混合主剂与固化剂，使用动力工具搅拌均匀

Mixing Ratio	Base/Hardener=9/1(by weight)					
混合比例	主剂/固化剂=9/1（质量比）					
Pot life	5℃	20℃	30℃			
混合使用期	8hrs	6hrs	3hrs			
Application Methods	Airless spray, air spray, brush and roller					
施工方法	无气喷涂、空气喷涂、刷涂和滚涂					
	Airless spray 无气喷涂					
	Nozzle tip	喷嘴尺寸	0.43mm-0.53mm			
	Nozzle pressure	出口压力	≥15Mpa			
	Thinning ratio	稀释比率	0-5% by volume（体积比）			
	Brush/Roller 刷涂、滚涂					
	Thinning ratio	稀释比率	5-10% by volume（体积比）			
Thinner	Epomarine Thinner #20					
稀释剂	环氧稀释剂#20					
Drying time & Overcoating interval	Temperature	温度	5℃	10℃	20℃	30℃
干燥时间&涂装间隔	Surface dry	指触干燥	5hrs	4hrs	3hrs	2hrs
	Touch dry	半硬干燥	48hrs	24hrs	16hrs	12hrs
	Min. interval	最小涂装间隔	48hrs	36hrs	24hrs	16hrs
	Max. interval	最大涂装间隔	7days	7days	7days	7days
Typical undercoat	Bare steel, SD ZINC 500 etc.					
适用下涂	裸钢，环氧富锌涂料 500 等					
Typical topcoat	RETAN 6000, KANPE FLON HD or according to the coating system of Cosco Kansai.					
适用上涂	聚氨酯面漆 6000，氟碳面漆或参考我司涂装配套					
STORAGE	Store in dry, cool condition and away from sources of heat and ignition. Containers must be kept tightly closed.					
贮存	贮存于干燥阴凉的环境中，远离热源及火源。包装桶必须保持封闭。					
Shelf life	12 months from date of production (25℃)					
贮存期限	自生产之日起 12 个月（25℃）					
DISCLAIMER	The information given on this sheet is to the best of our knowledge and accurate at the time of issuing. Since conditions of use are beyond the manufacturer’s control, information contained herein is without warranty, implied or otherwise, and the suitability of the material for the use contemplated is the sole responsibility of the buyer. The information contained on this data sheet is subject to modification at any time due to our policy of modification and product development. Please check this date sheet is current prior to using the product.					
提请注意	本说明书所提供信息均为目前我方所掌握最全面正确的资料,鉴于产品使用条件非我方所能控制，此中信息不含担保，即仅在选取产品上对买方负责。由于我公司产品及生产工艺的不断发展，本说明书的内容也会随时进行更改，此中所有信息均以我方确认为主。产品使用前，请确认所持说明书为最新版本。					