



技术说明书

TECHNICAL DATA SHEET

021-50568299

服务时间 9:00 - 21:00



www.rich-tech.net

在线选品 / 资料下载 / 色号查询 / 行业资讯




扫码加企业微信

报价、销售及技术支持

本资料由 锐亿奇工业科技（上海）有限公司 整理提供，仅供客户选型参考，具体性能参数以原厂最新版本为准
严禁转载本资料，请访问锐亿奇官网获取最新资讯

AMENICOAT ZINC PRIMER(S)

Product Description	Two-component waterborne paint based on waterborne epoxy resin and hardener, added zinc dust.	
Recommended Use	As self-emulsifying primer can be used for steel freight container.	
Physical Properties		
Color	Grey and other colors	
Mixing ratio	Base/Hardener = 4/1 (by wt.)	
Theoretical Volume by Weight, %	77	
Specific gravity	2.20-2.30	
VOC	<280 g/L	
Film thickness	Dry: 30 microns/coat	Wet : 60 microns/coat
Theoretical Coverage	0.039 Kg/m ² /10 microns	
Storage	Store in dry, cool conditions, and away from sources of heat & ignition. Containers must be kept tightly closed.	
Storage Temperature	5°C-35°C	
Shelf life	Base: 6months	Hardener: 6months
	Shelf life: Subject to re-inspection thereafter.	
Application		
Application Temperature	15°C-35°C	
Pot life	4hrs	
Application Methods	Airless spray, air spray , brush , roller	
Thinner	Water	
Drying & Oven schedule	20min@70°C	



扫码加企业微信
报价、销售及技术支持